

Technical Data Sheet



HILITE

An ISO/TS 16949:2009, ISO 14001 : 2004, OHSAS 18001: 2007 Certified Company

HAF 2000 NON ASBESTOS MILL BOARD MATERIAL

General properties and application :

HAF 2000 : It is a non asbestos millboard material to be used as a filler material between metal sheets mainly used for exhaust manifold and heat shield applications. Max Operating temperature 300°C

Technical Data

Specification values determined in accordance with ASTM F-104 Type 7

Physical Properties	Unit	Typical Value
Density	gm/cc	1.15-1.25
Compressibility at 70 kg/cm ²	%	15-25
Recovery (Min)	%	25
Tensile Strength (Min)	kg/cm ²	25
Loss of Ignition at 850°C	%	21

Availability	Unit	Standard Size
Thickness range	mm	0.25 -1.50 in Rolls above 1.00 -1.50 in sheets
Roll width	mm	1000 ± 20
Roll Weight	Kgs	50
Sheet Size	mm	1000 X 1000

All information data quoted are based on experience in production of sealing elements. However, In view of the wide variety of possible installation and operating conditions one can not draw final conclusions in all application cases regarding the behaviors in a gasket joint.

Whenever there is any doubt, our staff will be pleasure to assist you in finding the optimum sealing solutions.

Hilite Industries Pvt. Ltd.

B-1, Site No.1 B.S. Road Industrial Area Ghaziabad-201001 (U.P.) INDIA

Ph. +91 0120-4144500