

# Technical Data Sheet



# HILITE

An ISO/TS 16949:2009, ISO 14001 : 2004, OHSAS 18001: 2007 Certified Company

## HILITE 9000 NON ASBESTOS GRAPHIL MATERIAL

### General properties and application :

**HILITE 9000** : It is a dark grey colour material with composition of high temperature minerals like graphite & mica. It is recommended for use a filler material for spiral wound Gasket. Max Operating temperature 200°C

### Technical Data

Specification values determined in accordance with ASTM F-104 Type 7

Physical Properties	Unit	Typical Value
Density	gm/cc	1.15 ± 0.05
Compressibility at 350 kg/cm <sup>2</sup>	%	15-25
Recovery (Min)	%	20
Tensile Strength (Min)	kg/cm <sup>2</sup>	50
Loss of Ignition at 850°C (Max)	%	35

### Fluid absorption

Weight Increase			
ASTM Oil No. 3	5 Hrs @ 150°C (Max)	%	50
ASTM Fuel B	5 Hrs @ 21 to 30°C (Max)	%	50
Water Distilled	5 Hrs @ 21 to 30°C (Max)	%	60

Thickness Increase			
ASTM Oil No. 3	5 Hrs @ 150°C (Max)	%	10
ASTM Fuel B	5 Hrs @ 21 to 30°C (Max)	%	10
Water Distilled	5 Hrs @ 21 to 30°C (Max)	%	30

Availability	Unit	Standard Size
Thickness range	mm	0.50 -1.00 in Rolls
	mm	Above 1.00 -1.50 in sheets
Roll width	mm	1000 ± 20
Roll Weight	Kgs	50
Sheet Size	mm	1000 X 1000

All information data quoted are based on experience in production of sealing elements. However, In view of the wide variety of possible installation and operating conditions one can not draw final conclusions in all application cases regarding the behaviors in a gasket joint.

Whenever there is any doubt, our staff will be pleasure to assist you in finding the optimum sealing solutions.

### Hilite Industries Pvt. Ltd.

B-1, Site No.1 B.S. Road Industrial Area Ghaziabad-201001 (U.P.) INDIA

Ph. +91 0120-4144500