Technical Data Sheet



An ISO/TS 16949: 2009, ISO 14001:2004, OHSAS 18001: 2007 Certified Company

HILITE AFM 330 NON ASBESTOS GASKET JOINTING SHEET

330 Hilite

e AFM 330 Hilite AFM AFM 330 Hilite AFM

FM 330 Hilite AF

330 Hilite

Applications:

Gasket material with controlled swell properties in oil, wide range of application in automotive and chemical industry. Suitable to seal off hydraulic, engines, transmission and refrigerating oils as well as other hydrocarbons. Also applicable for joints with low sealing pressure like housing, valve covers, oil pans etc.

General data:

Material Composition

Aramid Fibre, Mineral Fiber (Type of fibres)

Binders SBR

OPERATING CONDITION

Max.Peak Temp 400°C

Max. Continuous Temp 270°C Max.Continuous Temp.with steam 240°C


Max. Operating Pressure 150 Kg/cm²

Physical Properties:

The following Information applies to material thickness 2.0 mm.

S.NO.	PROERTIES	TEST METHOD	UNIT	SPECIFIED VALUE
1.	DENSITY		gm/cm³	1.70 - 2.00
2.	TENSILE STRENGTH			
	(a) ACC to ASTM F152(ACROSS GRAIN)		N/mm²	≥ 12
	(b) ACC to DIN52910 (ACROSS GRAIN)		N/mm²	≥ 9
3.	COMPRESSIBILITY	ASTM F36J	%	5 – 15
4.	RECOVERY	ASTM F36J	%	≥ 50
5.	FLUID ABSORPTION	ASTM F 146		
	(a) IN ASTM OIL NO. 3			
	INCREASE IN MASS		%	8-30
	INCREASE IN THICKNESS		%	8-30
	(b) IN FUEL B	ASTM F 146		
	INCREASE IN MASS		%	8-30
	INCREASE IN THICKNESS		%	8-30
	(c) IN WATER/ANTIFREEZE	ASTM F 146		
	INCREASE IN MASS		%	15
	INCREASE IN THICKNESS		%	7
6.	IGNITION LOSS	DIN 52911	%	≤ 35
7.	SEALABILITY AGAINST Nitrogen	DIN 3535	cm³/min.	≤ 1.0
8.	STRESS RESISTANCE			
	16h 300°C	DIN 52913	N/mm²	~ 20
	16h 175°C	DIN 52913	N/mm²	~ 30

Standard Sheet Size		1500x2000 mm, 1500x4000mm, 1500x1500mm 1500x4500 mm, 1500x3000mm, 2000x3000 mm
Thickness		0.25 mm to 6.00 mm (For Non-Metallic Range) 0.80 mm to 6.00 mm (For Metallic Range)
Tolerance Thickn		< 1mm = ± 0.10 mm > 1mm = ± 10%
	Length	± 50 mm
	Width	± 50 mm



All data quoted above are based on years of experience in production & operation of sealing elements, in view of the wide variety of possible installation & operating conditions one can not draw final conclusion in all application cases regarding the behaviour in gasket joint. The data may not therefore, be used to support any warranty claims.

Should you have any doubts about the choice of gasket material, please refer to us. Our engineering cell will be happy to assist

you.

HILITE Industries Pvt. Ltd

Phone: 0091-120-4144500, 2700879 Fax: 0091-0120-2703385 email: hi-lite@vsnl.net Website www.hilite.co.in